

# NITRIDERM® ULTRA ORANGE™

## Nitrile Exam Gloves Extra Protection Series 199


Orange - The universal symbol for caution. Ideal for EMS, police and fire, hazmat functions, spills, etc. This medium weight nitrile glove is extremely elastic and comfortable while providing the tensile strength required for these demanding procedures. Polymer interior for rapid donning. Textured finish for an excellent grip even in the presence of moisture.

Characteristics: Powder-Free, Non-Sterile, Orange color

SIZE	ITEM NO.
XS	199050
S	199100
M	199200
L	199300
XL	199350
XXL	199400
XXXL	199450

XS-XL: 100 Gloves/Box, 10 Boxes/Case

XXL-XXXL: 80 Gloves/Box, 10 Boxes/Case



### Features:

- Textured Finish = an Improved Wet/Dry Grip
- Low Modulus = a Softer, More Comfortable Fit
- Non-Latex = No Risk of Latex Allergens

Manufactured in compliance with multiple international standards, including ASTM D6319, ASTM D5151, ASTM F1671, and ASTM D6978

### Tested for use with Chemotherapy Drugs as per ASTM D6978

Standard Practice for Assessment of Medical Gloves to Permeation by Chemotherapy Drugs

Minimum Breakthrough Detection Time in Minutes:

Azacitidine (25.0 mg/ml)	>240	Ifosfamide (50.0 mg/ml)	>240
Carboplatin (10.0 mg/ml)	>240	Irinotecan (20.0 mg/ml)	>240
Carmustine (3.3 mg/ml)	12.9	Methotrexate (25.0 mg/ml)	>240
Cisplatin (1.0 mg/ml)	>240	Mitomycin C (0.5 mg/ml)	>240
Cyclophosphamide (20.0 mg/ml)	>240	Mitoxantrone (2.0 mg/ml)	>240
Dacarbazine (10.0 mg/ml)	>240	Oncovin (1.0 mg/ml)	>240
Docetaxel (10.0 mg/ml)	>240	Oxaliplatin (5.0 mg/ml)	>240
Doxorubicin Hydrochloride (2.0 mg/ml)	>240	Paclitaxel (6.0 mg/ml)	>240
Epirubicin (2.0 mg/ml)	>240	Thiotepa (10.0 mg/ml)	45.0
Etoposide (20.0 mg/ml)	>240	Vincristine Sulfate (1.0 mg/ml)	>240
Fluorouracil (50.0 mg/ml)	>240	Vinorelbine (10.0 mg/ml)	>240
Gemcitabine (38.0 mg/ml)	>240	Also Tested: Fentanyl Citrate (100 mcg/2ml)	>240

Please note that Carmustine and Thiotepa have extremely low permeation times of 12.9 minutes and 45.0 minutes respectively.

Warning: Do not use with Carmustine. Warning: Do not use with Thiotepa.

Caution: In compliance with ASTM D6978, the testing conditions used are intended to approximate the worst-case conditions for clinical use. Testing was conducted on single layer glove material. It is the users' responsibility to determine the applicability of these gloves for their intended use with chemotherapy drugs.

Tensile Strength & Elongation	Before Aging	After Accelerated Aging
Tensile Strength (Mpa)	32	27
ASTM Requirement Min. (Mpa)	14	14
Elongation (%)	650	480
ASTM Requirement Min. (%)	500	400

Average Length	9.5 in ♦ 240 mm
Average Palm Thickness	3.5 mil ♦ 0.09 mm
Average Finger Thickness	4.3 mil ♦ 0.11 mm



**Intertek**

Innovative Healthcare Corporation is certified to ISO 13485:2016 QMS for medical devices.



**INNOVATIVE  
HEALTHCARE  
CORPORATION**

www.ihc-solutions.com

1-800-272-1533

*Product Solutions You Trust*

View this product  
on our website:

